



VYPET VNT 835

PET 35% Glass/Mineral Reinforced

Vypet VNT 835 is a 35% mineral and fiberglass reinforced PET injection molding compound designed for structural applications.

Features

- High temperature performance
- Low warp
- Excellent dimensional stability

Typical Applications

- Grill retainers
- Lamp holders

Typical Resin Properties ^(a)	ASTM Method	Typical values
Density at 23°C, g/cm ³	D792	1.56
Viscosity at 1000 Hz, Pa*sec	D3835	227
Izod, notched, 23°C, J/m	D256	72.7
Tensile Strength @Yield, MPa	D638	117.8
Elongation @ Break, %	D638	3.51
Flexural Strength, MPa	D790	181
Flexural Modulus (1.3mm/min), MPa	D790	9,735
HDT @ 1820 kPa, °C	D648	213

(a) The property values are based on a limited number of tests and, therefore, should not be construed as product specifications.

Processing Guidelines

Drying

The Vypet VNT grades process easily but must be thoroughly dried before molding, preferably in a dehumidifying desiccant hopper dryer, operating with an air flow rate of min1.0 CFM/lb, dew point of -18°C or lower. The material should be dried at 121°C (250° F) for 4 hours and the humidity content of the material should be maintained below 0.02% during molding.

Molding

Vypet VNT products have a relatively wide processing window with barrel temperature settings as following:

- Feed zone: 260-270°C (500-520°F)
- Middle zone: 265-280°C (510-530°F)
- Front zone: 271-293°C (520-560°F)
- Nozzle: 280-299°C (530-570°F)
- Melt temperature: 280-290°C (530-550°F)
- Mold temperature: 94-122°C (200-250°F)

Other Molding Parameters

- Injection Pressure: 8000-12000 psi
- Injection Speed: Fast to improve aesthetics and reduce stress
- Back Pressure: Low (25-50 psi)
- Screw Speed: 50-75 rpm



ISO 17025



Conseil canadien des normes
Standards Council of Canada

MN46r1 DS VYPET VNT 835 - Rev2

8800, Crescent 1 Ville d'Anjou, (Québec) Canada H1J 1C8

Tel. : 514-354-5757 Fax. : 514-354- 3087 Email : lavergne@lavergne.ca

The information in this technical datasheet is, to our knowledge, true and accurate. Inasmuch as we have no control over the many different conditions under which this information and our products may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our products in any given situation. Users of our products should make their own tests to determine the suitability of each product to their particular application. The products are sold without warranty and the buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. Statements concerning the possible use of our products are not intended as recommendations to use our products in conflict with any existing patents covering any materials or its use